



شركة أبولو لكيمائيات الأبنية Apollo For Construction Chemicals

APOLLO ROOF W600 Method Statement (Single Liquid Component, Acrylic Waterproof Coating for Roofs)

Section A: General Comments

High temperature working

It is suggested that, for temperatures above 40°C, the following guidelines are adopted as good working practice:

- (i) Unmixed materials and equipment should be stored in cool, dry place and away from direct sunlight.
- (ii) Plan for enough material, tools and labors to avoid any stoppage during the application process.
- (iii) Avoid application through peak temperatures of the day.
- (iv) Ensure proper and adequate ventilation.

Equipment

It is suggested that the following list of equipment is adopted as a minimum requirement:

Personal protection : Protective overalls, thick gloves, goggles and face mask
Preparation equipment : Stiff wire brush, Soft brush, Air compressor, mixer
Application equipment : Brush, roller or airless spray

Section B: Application

1.0 Preparation

- 1.1 All surfaces to be waterproofed must be clean, sound, dry, and free of all surface contaminations such as form release agents, curing compounds, laitance, dust, dirt, cavities, projecting nibs, etc.



شركة أبولو لكيماويات الأبنية

Apollo For Construction Chemicals

- 1.2 If present, laitance should be removed from concrete by grit blasting or wire brushing.
- 1.3 Ensure the substrate surface is smooth and free from cracks. Any surface imperfections shall be repaired using a suitable cementitious repair mortar.

Notes:

- *New concrete structures need to cure and dry for at least 14 days.*
- *APOLLO ROOF W600 should not be applied on surfaces expected to suffer from rising dampness or relative humidity greater than 75%.*
- *It is not recommended to apply this material if the ambient temperatures might drop to below 5°C.*

2.0 Priming

- 2.1 For porous concrete substrates, NASA Primer products should be used at the rate of 5 m²/liter allowed to dry for 4 hours at 25°C before applying the Apollo Roof W600.

3.0 Application

- 3.1 Mix the material well before use using a low speed (300 rpm) mixer or electric drill.
- 3.2 Apply the first coat with brush, roller or airless spray machine at a rate of 1.5 - 2.0 m²/liter.
- 3.3 Leave the first coat to cure for 4 hours at 25°C.
- 3.4 Apply the second coat at a rate of 1.5 – 2.0 m²/liter perpendicular to the first coat. The second coat should be applied within 12 hours from the application of the first coat.

Note: For substrates which will be subjected to pedestrian traffic, it is recommended to use fiberglass scrim reinforcement, embedded firmly in the second coat while still wet, and a third coat should be applied at the same coverage rate.



شركة أبولو لكيمائيات الأبنية Apollo For Construction Chemicals

4.0 Cleaning

- 4.1 Tools and equipment can be cleaned **immediately** before curing with clean water. Cured material must be removed mechanically.

Section C: Approval and variations

This method statement is offered by Apollo for construction chemical as a 'standard proposal' for the application of **APOLLO ROOF W600**. It remains the responsibility of the Engineer to determine the correct method for any given application. Where alternative methods are to be used, these must be submitted to Apollo for construction chemical for approval, in writing, prior to commencement of any work. Apollo for construction chemical will not accept responsibility or liability for variations to the above method statement under any other condition.